

Serial No. 08/857,585

16. (New) The adsorbent structure of claim 3, wherein the ratio of (a) to (b) ranges from 10:90 to 85:15.

~~17. (New) The adsorbent structure of claim 3, wherein said high-silica zeolite in said adsorbent structure has a BET specific surface area after a heat treatment of 1,100°C of at least 30 m²/g.~~

LI 18. (New) The adsorbent structure of claim 3, wherein said high-silica zeolite in said adsorbent structure has a BET specific surface area after a heat treatment of 1,100°C of from 30 to 350 m²/g.

19. (New) A process for treating exhaust gases comprising passing said exhaust gases through an adsorbent structure of claim 3 to remove hydrocarbons therefrom.